

How does Toluene Dissolve Low-Molecular-Weight Polystyrene?

Project Manager
Dr.-Ing. Valentina Marcon

Principal Investigator
Prof. Dr. Nico van der Vegt

Project Term
2015 - 2015

Project Areas
Physical and Theoretical Chemistry

Clusters
Lichtenberg Cluster Darmstadt

Institute
Physikalische Chemie

University
Technische Universität Darmstadt




Fig. 1: Left: Simulation box after 60 ns atomistic molecular dynamics simulation. Polystyrene chains are shown in red, toluene molecules in blue. Highlighted are the solvated polystyrene molecules and the toluene molecules that diffused in the polymer matrix. Right: Schematic description of the sequence of phenomena taking place. The simulation box on the left represents the atomistic snapshot of the Outside-In mechanism.

Introduction

Many industrial applications, like nanolithography, gas separation based on membranes, plastic recycling and drug delivery, rely for their performance on a deep knowledge of the mechanisms involved in polymer dissolution. When a solvent gets in contact with a polymer, two distinct processes occur: (I) the solvent diffuses into the polymer and (II) the polymer chains at the surface get solvated. The diffusion of the solvent and the consequent formation of a swollen layer (i.e. a layer with a lower polymer density due to the presence of the solvent) favour the detachment of the chains from the surface.

Recent studies have shown how polymer dissolution can be relevant also for wetting properties. Even if much is understood about the wetting of non-soluble substrates, much is still to be understood in the case of soluble substrates.

Due to the experimental difficulties, the penetration of solvent in thin polymer films is rarely investigated. However the molecular level details of polymer surfaces are accessible also by computer simulations.

Methods

We investigated with atomistic simulations[1] the swelling of low-molecular-weight polystyrene induced by toluene, a solvent for polystyrene. The simulation box is shown in the left panel of Fig.1. We overcome the intrinsic difficulties of obtaining an equilibrated atomistically detailed polymer surface structure with a hierarchical simulation approach. Based on a low-

resolution model[2] for polystyrene we have obtained polystyrene chain conformations and chain packing at the surface, which are independent from our initial setup[3]. With an inverse-mapping procedure[4] we then obtained the high-resolution atomic-scale picture of the polymer.

Results

In our simulations we were able to track the real time evolution of the processes involved when a glassy polymer substrate is brought in contact with a solvent. We observed in our simulations that the polymer chains detach from the surface within a few nanoseconds, during which the solvent enters a nanometer thick surface layer. This, extremely rapid, surface swelling is probably favoured by the roughness of the disordered polymer surface. After this initial swelling, both the dilution of the chains due to the penetration of the solvent in the polymer film and the detachment of the chains from the surface take place concurrently[5]. The schematic time sequence is shown in the right panel of Fig.1.

Outlook

An accurate quantification of the kinetics of dissolution is at the atomistic scale however not possible. In order to obtain a better statistics and to investigate the dissolution on longer polymer chains, simulations with low-resolution models are necessary. We are currently developing models[6], which keep the original relative dynamics of the atomistic system. These models will then be used to quantify the kinetics of dissolution.

Reference

- [1] B. Hess, C. Kutzner, D.V. van der Spoel, and E. Lindahl (2008), GROMACS 4: Algorithms for Highly Efficient, Load-Balanced, and Scalable Molecular Simulation. *Journal of Chemical Theory and Computation* 4: 435-447. <https://doi.org/10.1021/ct700301q>
- [2] D. Fritz, V.A. Harmandaris, K. Kremer, and N.F.A. van der Vegt (2009), Coarse-Grained Polymer Melts Based on Isolated Atomistic Chains: Simulation of Polystyrene of Different Tacticities. *Macromolecules* 42: 7579-7588. <https://doi.org/10.1021/ma901242h>
- [3] V. Marcon, D. Fritz, and N.F.A. van der Vegt (2012), Hierarchical modelling of polystyrene surfaces. *Soft Matter* 8: 5585-5594. <http://dx.doi.org/10.1039/C2SM25342A>
- [4] D. Fritz, C.R. Herbers, K. Kremer, and N.F.A. van der Vegt (2009), Hierarchical modeling of polymer permeation. *Soft Matter* 5: 4556-4563. <https://doi.org/10.1039/B911713J>
- [5] V. Marcon V. and N.F.A. van der Vegt (2014), How does low-molecular-weight poly-styrene dissolve: osmotic swelling vs. surface dissolution *Soft Matter*, 10: 9059-9064. <https://doi.org/10.1039/C4SM01636J>
- [6] G. Deichmann, V. Marcon, and N.F. A. van der Vegt (2014), Bottom-up derivation of conservative and dissipative interactions for coarse-grained molecular liquids with the conditional reversible work method *J. Chem. Phys.*, 141: 224109. <https://doi.org/10.1063/1.4903454>

Last Update: 2022-07-08 11:08