

High Throughput Screening of Magnetic Antiperovskites

Project Manager
Harish Kumar Singh

Researchers
Dr. Ingo Opahle

Principal Investigator
Jun. Prof. Dr. Hongbin Zhang

Project Term
2018 - 2019

Project Areas
Theoretical Condensed Matter
Physics

Clusters
Lichtenberg Cluster Darmstadt

Software
VASP

Institute
Materials Science

University
Technische Universität Darmstadt




Figure 1: Ternary phase diagram of Co-Pd-N.

Introduction

Analogous to perovskites, the antiperovskites (APVs) are also one of the most commonly explored materials in recent years because of their remarkable properties such as superconductivity, nontrivial topological nature, spin glass behavior, barocaloric effect, thermoelectric, magnetostriction, negative thermal expansion, and piezomagnetism.[1-8] Particularly, magnetic APVs with transition-metal show many fascinating physical properties, resulting from the cooperative interplay among the lattice, spin, and charge degrees of freedom. A prominent example is the barocaloric effect observed in Mn_3GaN ,[4] which is originated from the geometric frustration associated with the noncollinear antiferromagnetic spin configuration.

Methods

An extended version of the high-throughput environment (HTE) is used to determine the thermodynamical and mechanical stability. DFT calculations are performed with the projector augmented wave method as implemented in the VASP package. The energy cutoff is 500 eV, and $14 \times 14 \times 14$ k-points are used for the Brillouin zone integrations. The exchange-correlation functional is approximated using the generalized gradient approximation (GGA) as parametrized by Perdew–Burke–Ernzerhof (PBE). The lattice dynamics of APVs is studied in the framework of the harmonic approximation, where

the phonon spectra are obtained using the frozen phonon approach with the Phonopy and VASP codes.

Results

We carried out systematic high throughput screening on 620 antiperovskite (APV) compounds using first-principles calculations. Three stability criteria such as thermodynamical stability, mechanical stability, and lattice dynamic stability were evaluated. After validating our calculations using 79 existing APV materials, it is identified that 11 novel compounds can be stabilized in the cubic APV structure. This paves the way to design more magnetic materials, and we hope our work will stimulate more experimental and theoretical efforts to investigate interesting properties of APV compounds. Particularly, in order to consider all competing phases, the concept of the convex hull is used. The convex hull is constructed by linear interpolation of the formation energies of known phases of a system in order to calculate the formation energy for every composition. For magnetic APVs, all competing phases stored in our in-house HTE database are considered. It contains among others about 3900 different experimentally reported binary and ternary phases relevant for the calculation of ternary phase diagrams with the magnetic 3d elements $M = \text{Cr, Mn, Fe, Co and Ni}$. In addition, about 5,200 phases available in the materials project database for these systems are included. Such calculations enable us to construct ternary phase diagrams, as shown in Fig. 1 for the Co-Pd-N system where the Co_3PdN is a stable predicted phase. In combination with phonon spectra, the Gibbs free energy at finite temperatures can be evaluated, which can provide essential inputs for future thermodynamic assessment of the ternary phase diagrams using CALPHAD to predict novel phases.

Publications

Singh, H. K.; Zhang, Z.; Opahle, I.; Ohmer, D.; Yao, Y.; Zhang, H.: High-Throughput Screening of Magnetic Antiperovskites. *Chemistry of Materials* 2018 30 (20), 6983-6991.
<https://doi.org/10.1021/acs.chemmater.8b01618>

Reference

[1] He, T.; Regan, K. A.; Rogado, N.; Hayward, M. A.; Haas, M. K.; Slusky, J. S.; Inumara, K.; Zandbergen, H. W.; Cava, R. J.: Superconductivity in the Non-Oxide Perovskite MgCNi₃. *Nature* 2001, 411, 6–8.
<https://doi.org/10.1038/35075014>

[2] Yu, R.; Weng, H.; Fang, Z.; Dai, X.; Hu, X.: Topological Node-Line Semimetal and Dirac Semimetal State in Antiperovskite Cu₃PdN. *Phys. Rev. Lett.* 2015, 115, 036807–036811.
<https://doi.org/10.1103/PhysRevLett.115.036807>

[3] Zu, L.; Lin, S.; Lin, J.; Yuan, B.; Kan, X.; Tong, P.; Song, W.; Sun, Y.: Observation of the Spin-Glass Behavior in Co-Based Antiperovskite Nitride GeNCo₃. *Inorg. Chem.* 2016, 55, 9346–9351.
<http://dx.doi.org/10.1021/acs.inorgchem.6b01462>

[4] Matsunami, D.; Fujita, A.; Takenaka, K.; Kano, M.: Giant Barocaloric Effect enhanced by the Frustration of the Antiferromagnetic Phase in Mn₃GaN. *Nat. Mater.* 2015, 14, 73–78.
<https://doi.org/10.1038/nmat4117>

[5] Lin, S.; Tong, P.; Wang, B.; Lin, J.; Huang, Y.; Sun, Y.: Good Thermoelectric Performance in Strongly Correlated System SnCCo₃ with Antiperovskite Structure. *Inorg. Chem.* 2014, 53, 3709–3715.
<https://doi.org/10.1021/ic500026t>

[6] Shibayama, T.; Takenaka, K.: Giant Magnetostriction in Antiperovskite Mn₃CuN. *J. Appl. Phys.* 2011, 109, 07A928–07A930.
<https://doi.org/10.1063/1.3560892>

[7] Takenaka, K.; Takagi, H.: Giant Negative Thermal Expansion in Ge-Doped Anti-Perovskite Manganese Nitrides. *Appl. Phys. Lett.* 2005, 87, 261902–261904. <https://doi.org/10.1063/1.2147726>

[8] Zemen, J.; Gercsi, Z.; Sandeman, K. G.: Piezomagnetism as a Counterpart of the Magnetovolume Effect in Magnetically Frustrated Mn-Based Antiperovskite Nitrides. *Phys. Rev. B: Condens. Matter Mater. Phys.* 2017, 96, 024451–024458.
<http://dx.doi.org/10.1103/PhysRevB.96.024451>

Last Update: 2022-04-29 17:12