

Redox Chemistry of Ternary Graphite Intercalation Compounds

Project Manager
Dr. Olena Lenchuk

Principal Investigator
Prof. Dr. Doreen Mollenhauer

Project Term
2017 - 2018

Project Areas
Physical and Theoretical Chemistry

Clusters
Lichtenberg Cluster Darmstadt


Software
VASP

Institute
Institute of Physical Chemistry

University
Justus Liebig University Giessen

Funded by

Deutsche Forschungsgemeinschaft



Introduction

Sodium-ion batteries (SIBs) are considered as alternatives to lithium-ion batteries (LIBs), showing a potential in reducing the material cost and advancing from the same charge storage mechanisms as in LIBs [1-5]. The current project is aimed to investigate the structure and thermodynamic stability of alkali metal - graphite intercalation compounds (AM-GICs), which are formed during alkali metal intercalation into graphite. The thermodynamically stable GICs with high AM-content possessing the composition of AMC_6 or AMC_8 exist for lithium (LiC_6), potassium (KC_8), rubidium (RbC_8) and cesium (CsC_8) [6]. For sodium, however, only few low-concentration Na-GICs have been reported [7-8]. Na-GICs compounds are still a matter of debate. The working hypotheses of the observed behaviour are related to the structural deformation of the graphite during sodium intercalation as well as to the differences in the binding nature between alkali metals and graphite. Here, we present a small part of our study.

Methods

In our research, we first focused on the systematic investigation of the structure and energetics of the binary GICs at different stages (from stage-I to stage-IV) and various concentrations of the intercalated lithium and sodium ions (from AMC_6 to AMC_{72}). For this purpose, we performed density functional theory (DFT) [9-10] calculations with periodic boundary conditions. For the investigated models, dispersion correction to the DFT energy (DFT-D3 method, proposed by Grimme et al. [11-12]), was used for the description of the van der Waals interactions in AM-GICs. The alkali metals were located on top positions (denoted as "α" in Figure 1), whereas the AB- and AA-stacking of the graphite interlayers was considered. Atomic structures of the investigated AMC_6 and AMC_{12} compounds are shown in Figure 1.

Results

The thermodynamic stability of different AM-GICs was evaluated

by means of the formation energy, shown in Figure 2. Our results suggest that a transition from AB- to AA-stacked graphite takes place upon increasing the alkali metal concentration. This transition is observed for stage-II AM-GICs in the concentration range between $x = 16$ and $x = 32$. This finding is also consistent for the investigated alkali metals, lithium and sodium.

Discussion

Negative values of the formation energy (see Figure 2) indicate that binary GICs are stable with respect to the AB-stacked graphite and the bulk alkali metal. Our results indicate that the intercalation of Li into graphite is always energetically preferred. The driving force for Li intercalation depends on the mutual distribution of Li atoms (its concentration and stage). The formation energy of Na-GICs also varies depending on the concentration of Na atoms, but in contrast to Li, intercalation of Na atoms into graphite is always determined to be thermodynamically unfavorable. The analysis of the bond distances in Li- and Na-GICs shows that stretching of the in-plane C-C bonds in the investigated compounds is negligibly small compared to the pristine graphite and the observed volume expansion upon AM intercalation is caused by the expansion of the graphite interlayers. Furthermore, the graphite interlayer distances are increased upon increasing the atomic radius of the intercalated alkali metals, namely up to 15 % for lithium and up to 40 % for sodium. The observed results are in reasonable agreement with experimental data [7-8] and other theoretical studies [13-14].

Outlook

In this report, we have presented calculations of the structure and thermodynamic stability of Li- and Na-graphite intercalation compounds by means of DFT calculations. Our results reveal that, in contrast to Li-GICs, Na-GICs are always thermodynamically unstable. The energy contributions considering the structural deformation and the binding strength in the compounds affect the stability of the Na-GICs [15].

Figures

Publications

Goktas, M.; Bolli, C.; Berg, E.J.; Novák, P.; Pollok, K.; Langenhorst, F.; v. Roeder, M.; Lenchuk, O.; Mollenhauer, D.; Adelhelm, P.: „Graphite as Cointercalation Electode for Sodium-Ion Batteries: Electrode Dynamics and the Missing Solid Electrolyte Interphase (SEI)“, Adv. Energy Mater. Vol. 8, 2018, 1702724 (11 p.) <https://doi.org/10.1002/aenm.201702724>

Lenchuk, O.; Adelhelm, P.; Mollenhauer, D.: "Comparative Study of Density Functionals for the Description of Lithium-Graphite Intercalation Compounds, Computational Chemistry, Vol. 40, 2019, P. 2400-2412 <https://doi.org/10.1002/jcc.26017>

Reference

- [1] Hwang, J.-Y.; Myung, S.-T.; Sun, Y.K.: Sodium-ion batteries: present and future, Chem. Soc. Rev. 46, (2017)
<http://doi.org/10.1039/C6CS00776G>
- [2] Islam, M.S.; Fischer, C.A. J.: Lithium and sodium battery cathode materials: computational insights into voltage, diffusion and nanostructural properties, Chem. Soc. Rev. 43, (2014)
<http://doi.org/10.1039/C3CS60199D>
- [3] Pan, H.; Hu, Y.S.; Chen, L.: Room-temperature stationary sodium-ion batteries for large-scale electric energy storage, Energy Environ. Sci. 6, (2013) <https://doi.org/10.1039/C3EE40847G>
- [4] Cabello, M.; Chyrka, T.; Klee, R.; Aragón, M.J.; Bai, X.; Lavela, P.; Vasylychenko, G.M.; Alcántara, R.; Tirado, J.L.; Ortiz, G.F.: Treasure Na-ion anode from trash coke by adept electrolyte selection, J. Power Sources 347, (2017) <https://doi.org/10.1016/j.jpowsour.2017.02.065>
- [5] Yabuuchi, N.; Kubota, K.; Dahbi, M.; Komaba, S.: Research Development on Sodium-Ion Batteries, Chem. Rev. 114, (2014)
<https://doi.org/10.1021/cr500192f>
- [6] Adelhelm, P.: Alternative Natrium, Nachr. Chem. 62, (2014)
<https://doi.org/10.1515/nachrchem-2014-1206>
- [7] Metrot, A.; Guerard, D.; Billaud, D.; Herold, A.: New results about the sodium-graphite system, Synthetic Met. 1(4), (1980)
[https://doi.org/10.1016/0379-6779\(80\)90071-5](https://doi.org/10.1016/0379-6779(80)90071-5)
- [8] Ge, P.; Foulletier, M.: Electrochemical intercalation of sodium in graphite, Solid State Ionics 28-30, (1988)
[https://doi.org/10.1016/0167-2738\(88\)90351-7](https://doi.org/10.1016/0167-2738(88)90351-7)
- [9] Hohenberg, P.; Kohn, W.: Inhomogeneous Electron Gas, Phys. Rev. B 136, 864-871, (1964)
<https://journals.aps.org/pr/abstract/10.1103/PhysRev.136.B864>
- [10] Sham, L. J.; Kohn, W.: One-Particle Properties of an Inhomogeneous Interacting Electron Gas, Phys. Rev. B 145, 10.1103/PhysRev.145.561, (1966) <https://journals.aps.org/pr/abstract/10.1103/PhysRev.145.561>
- [11] Grimme, S.; Antony, J.; Ehrlich, S.; Krieg, H.: A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H-Pu, J. Chem. Phys. 132, (2010)
<https://doi.org/10.1063/1.3382344>
- [12] Grimme, S.; Ehrlich, S.; Goerigk, L.: Effect of the damping function in dispersion corrected density functional theory J. Comput. Chem. 32, 2011, J. Comput. Chem. 32, (2011) <https://doi.org/10.1002/jcc.21759>
- [13] Wang, Z.; Selbach, S.M.; Grande, T.: Van der Waals density functional study of the energetics of alkali metal intercalation in graphite, RSC Adv. 4, (2014) <https://doi.org/10.1039/C3RA47187J>
- [14] Liu, Y.; Merinov, B.V.; Goddard III., W.A.: Origin of low sodium capacity in graphite and generally weak substrate binding of Na and Mg among alkali and alkaline earth metals, PNAS 113, (2016)
<https://doi.org/10.1073/pnas.1602473113>

Last Update: 2022-06-17 13:42