

# High Throughput Screening and Tuning of Magnetic Two Dimensional Materials

Project Manager  
Jun. Prof. Dr. Xinru Li

Principal Investigator  
Jun. Prof. Dr. Hongbin Zhang


Project Term  
2019 - 2020

Project Areas  
Theoretical Condensed Matter  
Physics

Software  
VASP, Quantum ESPRESSO

Additional Software  
Wannier90

University  
Technische Universität Darmstadt



## Introduction

The demand of minimization and feasibility of integration makes two-dimensional (2D) materials remarkable in promising technological applications, whereas due to the breaking of translational symmetry, the 2D materials Display distinct properties than the corresponding bulk materials thus they are fundamentally interesting. Early in 2011, the US federal government has launched the Materials Genome Initiative, aiming at developing and exploring materials design strategically based on theoretical calculations using the well developed density functional theory methods, to go beyond the conventional way of materials discovery based on try-and-error or empirical knowledge. Regarding designing 2D materials, Ashton et.al. have searched for layered materials based on bulk crystal structures database Materials Project and predicted over 600 thermally stable 2D monolayers. However, such 2D materials have only been investigated by standard density functional theory calculations, without characterizing detailed functional properties. Hence, a thorough high throughput first principles study on 2D materials supported by high performance computational resources are of high demand. In our current project, for those nonmagnetic 2D materials in 2D materials database, the main guideline to the characterization is based on the accurate calculation of the band gap, resulting in the classification of 2D materials into possible photocatalysts, thermoelectrics or topological materials and hence predictions for future energy applications. we have successfully classified These 2D materials according to electronic and magnetic properties by high throughput methods based on density functional theory.

## Methods

The self consistent band structure calculations are carried out by using the augmented plane wave method as implemented in the VASP code. Spin polarized calculations with large initial magnetic moments are done in order to select the materials with nonmagnetic ground state. Moreover, the effect of SOC is considered self-consistently in all the calculations. The maximally localized Wannier functions (MLWFs) are constructed automatically with out implementation of a poor-man's algorithm by using the Wannier90 code. The projectors are chosen by the integrated partial density of states (DOS), where only those orbitals with large enough weight around the Fermi energy are chosen. The energy window is determined by the number of projectors and total DOS, We define a descriptor  $\Sigma$ , which is essentially the least square difference function between the eigenvalues calculated by VASP and Wannier 90 at all k-points in the whole Brillouinzone, to Judge the quality of the MLWFs. It is observed  $\Sigma$  should be smaller than 0.01 in order to obtain reliable MLWFs. After successful constructions of the MLWFs, the Hamiltonian in the Wannier basis is used to evaluate the surface states and topological invariant.

## Results

we have identified four topologically nontrivial two dimensional (2D) materials out of 641 most stable systems in the 2D materials database. The HTP Screening is carried out based on the automated construction of maximally localized Wannier functions followed by explicit calculations of the surface states, where the Wannier centers are evaluated as a further verification of the nontriviality. The electronic structure of such non trivial materials is discussed in Detail together with the features in the crystal structure and relevant orbitals. The work about HTP screening of 2D TIs has been published in 2D Materials.

## Figures




Figure 1: Classification of 746 systems in the 2D materials database based on their electronic properties.




Figure 2: (a) Top and side view of the crystal structures of ZrBr monolayers. (b) Phonon dispersions. (c) Band structure without SOC, with SOC and obtained from MLWFs indicated by gray solid line, blue solid line and red dashed line, respectively. Insets show the zoom-in view of the orbital resolved band structure near the  $\Gamma$  point. (d) Band structure of the 1D ribbon with nontrivial edge states highlighted in red.

## Reference

- [1] Xinru, L.; Zeyang, Z.; Yugui, Y.; Hongbin, Z.: High throughput screening for two-dimensional topological insulators, 2D Mater. 5, 045023 (2018). [https://ui.adsabs.harvard.edu/link\\_gateway/2018TDM.....5d5023L/doi:10.1088/2053-1583/aadb1e](https://ui.adsabs.harvard.edu/link_gateway/2018TDM.....5d5023L/doi:10.1088/2053-1583/aadb1e)
- [2] Zeyang, Z.; Run-Wu Z.; Xinru L.; Klaus Koepf, Yugui Yao, and Hongbin Zhang, High-Throughput Screening and Automated Processing toward Novel Topological Insulators, J. Phys. Chem. Lett. 9, 6224 (2018). <https://doi.org/10.1021/acs.jpcclett.8b02800>

*Last Update:* 2022-04-27 18:01