

# Reinforcement of Cr-Mn-Fe-Co-Ni High Entropy Bulk Metallic Glasses: A Molecular Dynamics Study

Project Manager  
Daniel Thomas Utt

Researchers  
Marie J. Perera (née Charrier)

Principal Investigator  
Prof. Dr. rer. nat. Karsten Albe

Project Term  
2020 - 2021

Clusters  
Lichtenberg Cluster Darmstadt

Software  
LAMMPS

Institute  
Materials Science

University  
Technische Universität Darmstadt




Figure 1: Stress-strain curves of 3d-periodic CrMnFeCoNi High Entropy Bulk Metallic Glass (HE-BMG) and nanocrystal (NC) subjected to tensile loading at 50 K and a strain rate of  $10^8 \text{s}^{-1}$  and their respective deformation structures. The maximum stress required to nucleate a shear band in the HE-BMG is higher than the yield strength for dislocation nucleation in the NC. While the compositions are equal and both materials show metallic bonding, the structures are entirely different. On one hand, the structure of the HE-BMG is amorphous. The atoms, which are part of the shear band are coloured white. The NC on the other hand shows long range order. The grain boundary atoms are coloured white. The atoms in the grain are coloured according to their crystalline structure. Due to the deformation dislocations are introduced into the grains and hcp and fcc stacking faults form, coloured in red and green, respectively.

## Introduction

We investigate the CrMnFeCoNi (Cantor alloy)[1] high-entropy bulk metallic glass (HE-BMG). HE-BMGs are a new amorphous materials class, that combines the high entropy alloys (HEAs) with the metallic glasses (MGs). HEAs on one hand consist of more than five elements at near equiatomic concentrations [2]. MGs on the other hand are amorphous metallic alloys that are rapidly quenched from the melt such that crystallization is kinetically hindered. They exhibit a high strength, hardness, and good corrosion resistance but are brittle at room temperature due to shear localization [3]. Preventing shear band formation and propagation in MGs is essential to prevent brittle failure. It has been shown that shear band propagation can be hindered by structural inhomogeneities [4] and we want to see whether the chemical fluctuations in the HE-BMG can further enhance its ductility. The CrMnFeCoNi system has so far only been studied in its crystalline form [5, 6]. We aim to investigate its mechanical properties as HE-BMG using large scale molecular dynamics simulations using LAMMPS, serving as a guide for experiment. The classical second neighbor modified embedded atom method (2NN MEAM) interatomic potential parameterized by Choi et al. [7] is used. The CrMnFeCoNi HE-BMG samples are prepared using melt quenching and the effect of the cooling rate on the resulting glass structure is studied. Afterwards, we investigate whether the deformation behavior of the HE-BMG under compressive and tensile load is different compared to the conventional CuZr BMG and the crystalline CrMnFeCoNi alloy. Last, we will look at the deformation behaviour of a CrMnFeCoNi HE-BMG sample, that already contains a shear band, in order to see, whether the nucleation of a second shear band can be induced.

## Methods

For all our simulations we used Molecular Dynamics implemented in the well-established, open source software package LAMMPS, a 'Large-scale Atomic/Molecular Massively Parallel Simulator' from Sandia National Laboratories. LAMMPS supports all features required for our research.

## Results

Fully amorphous CrMnFeCoNi HE-BMGs were successfully produced by melt quenching with rates below 10K/s. In the cooling curves a phase transition could be detected and the glass transition temperatures showed a cooling rate dependence. The characterization indicated an increase in structural and chemical short range order (SRO) for slower cooling rates. The HE-BMGs were subjected to tensile and compressive testing. At sufficiently low strain rates and temperatures shear banding could be observed. At room temperature the deformation was homogeneous. The strength of the HE-BMG was found to be higher than the strength of a simulated fcc CrMnFeCoNi nanocrystal (NC) and also shear band nucleation set in later compared to a conventional Cu-Zr glass. Re-straining of our HE-BMG did not lead to the formation of a

second shear band. Instead, the existent shear band continued to propagate.

## Discussion

The results show that the HE-BMG produced in this work is a promising new material, that should be investigated further. The chemical fluctuations in the material in combination with the amorphous structure lead to an extraordinarily high strength compared to the conventional Cu-Zr BMG and the CrMnFeCoNi NC. The structural SRO in the HE-BMG increases, the more time the glass has to relax, i.e. the slower the cooling rate. Besides an improved mechanical strength compared to conventional MGs, there are also promising approaches to improve the ductility. Therefore, in future research, nanostructured HE-BMG samples ought to be studied. They can be obtained from the growth of crystalline precipitates in the BMG or from high pressure compaction of amorphous spherical particles. In both cases, the additional interfaces provide obstacles to the shear band which leads to an increase in ductility.

## Reference

- [1] Cantor, B. et al.: Microstructural development in equiatomic multicomponent alloys, In: Materials Science and Engineering: A 375-377, pp. 213-218, 2004 <https://doi.org/10.1016/j.msea.2003.10.257>
- [2] Yeh J.-W. et al.: Nanostructured High-Entropy Alloys with Multiple Principal Elements: Novel Alloy Design Concepts and Outcomes, In: Advanced Engineering Materials 6.5, pp. 299-303, 2004 <https://doi.org/10.1002/adem.200300567>
- [3] Cheng, Y.Q.; Ma, E.: Atomic-level structure and structure-property relationship in metallic glasses, In: Progress in Materials Science 56.4), pp. 379-473, 2011 <https://doi.org/10.1016/j.pmatsci.2010.12.002>
- [4] Albe, K.; Ritter, Y.; Şopu, D.: Enhancing the plasticity of metallic glasses: Shear band formation, nanocomposites and nanoglasses investigated by molecular dynamics simulations, In: Mechanics of Materials. Nanostructured Materials 67, 2013 <http://dx.doi.org/10.1016/j.mechmat.2013.06.004>
- [5] Otto, F. et al.: The influences of temperature and microstructure on the tensile properties of a CoCrFeMnNi high-entropy alloy, In: Acta Mat. 61.15, pp. 5743-5755, 2013 <https://doi.org/10.1016/j.actamat.2013.06.018>
- [6] Gludovatz, B. et al.: A fracture-resistant high-entropy alloy for cryogenic applications, In: Science 345.6201, pp. 1153-1158, 2014 <https://doi.org/10.1126/science.1254581>
- [7] Choi, W. et al.: Understanding the physical metallurgy of the CoCrFeMnNi high-entropy alloy: an atomistic simulation study, In: npj Computational Materials 4.1, 2018 <https://doi.org/10.1038/s41524-017-0060-9>
- [8] Inoue, A. et al.: High-Strength Cu-Based Bulk Glassy Alloys in Cu-Zr-Ti-Be System, In: MATERIALS TRANSACTIONS 42.8 (2001), pp. 1800-1804. <https://doi.org/10.2320/matertrans.42.1800>
- [9] Şopu, D. et al.: Deformation behavior of bulk and nanostructured metallic glasses studied via molecular dynamics simulations, In: Phys. Rev. B 83, p. 100202, 2010 <https://doi.org/10.1103/PhysRevB.83.100202>
- [10] Brink, T.; Albe, K.: From metallic glasses to nanocrystals: Molecular dynamics simulations on the crossover from glass-like to grain-boundary-mediated deformation behaviour, In: Acta Materialia 156, pp. 205-214, 2018 <https://doi.org/10.1016/j.actamat.2018.06.036>
- [11] Adjaoud, O.; Albe, K.: Influence of microstructural features on the plastic deformation behavior of metallic nanoglasses, In: Acta Materialia 168, pp. 393-400, 2019 <https://doi.org/10.1016/j.actamat.2019.02.033>
- [12] Kalcher, C.: Creep of Cu-Zr metallic glasses and metallic glass composites: A molecular dynamics study, PhD thesis. Darmstadt: Technische Universität, 2019 <https://tuprints.ulb.tu-darmstadt.de/id/eprint/8610>

*Last Update:* 2022-04-27 16:58