

Molecular Dynamics Simulations of Nanoglasses

Researchers
Omar Adjaoud

Principal Investigator
Prof. Dr. rer. nat. Karsten Albe

Project Term
2015 - 2015

Project Areas
Materials Engineering

Clusters
Lichtenberg Cluster Darmstadt

Software
LAMMPS

Institute
Fachgebiet Materialmodellierung

University
Technische Universität Darmstadt




Fig. 1: Microstructure of metallic NGs. Glassy grains are shown with the blue color and glass-glass interfaces with yellow color.

Introduction

Metallic glasses (MGs) are of great technological interest because of their high strength and hardness [1]. However, when MGs are exposed to an external load then they fail catastrophically along a single shear band [2]. On a microscopic scale, shear bands in MGs are considered to be controlled by the activation of shear transformation zones that represents local shearing of approximately 100 atoms [3]. To avoid the catastrophic failure in MGs and improve their ductility, predeformed samples and glasses with nanocrystalline inclusions have been studied in the past [3,4]. The main findings of these studies is that the presence of such microstructural inhomogeneities in the samples prevent the formation of the shear band, which could cause catastrophic failure. Recently, a new class of MGs have been proposed, the so-called metallic nanoglasses (NGs) [5]. Metallic NGs have been produced by consolidating nanometer-sized glassy spheres which are prepared by inert-gas condensation [5,6] (Fig. 1). Recent experimental studies have shown that metallic NGs present enhanced ductility [5] and ferromagnetism [7] when compared with MGs. In addition, NGs are promising candidates as materials for medical applications [8].

Methods

The properties of materials are strongly controlled by their microstructure. Despite the improved properties of NGs, their microstructure is not well understood. Atomistic simulations are useful tools to gain insights on the atomic level into the structure

of a material. Several microstructural models for NGs have been proposed based on atomistic simulations. Although those models have offered explanations on the origin of enhanced ductility in NGs, a proper structural model which could explain the experimental observations on the structure of NGs is still lacking. We have performed large-scale molecular dynamics simulations, as implemented in the LAMMPS software [9], to investigate the microstructure of the NGs.

Results

Our results reveal that NGs are amorphous materials with inhomogeneous microstructure which consists of glassy grains connected with glass-glass interfaces (Figure). Structural analysis show that the glass-glass interfaces in NGs are characterized by a lack of short range order compared to MGs and a width of about 1 nm. In addition, they have a different composition than the glassy grains. The present microstructure for NGs is consistent with experimental analysis by means of small-angle X-ray scattering measurements and element mapping data on the Sc-Fe Ngs [5].

Outlook

In the future, we plan to perform molecular dynamics simulations to study the deformation mechanisms in NGs. It is proposed that the glass-glass interfaces prevent strain localization. We will perform a set of mechanical tests in order to get better understanding on how glass-glass interfaces in NGs influence their mechanical properties.

Reference

- [1] M. Telford (2004): The case for bulk metallic glass. Mater. Today 7, 36. [https://doi.org/10.1016/S1369-7021\(04\)00124-5](https://doi.org/10.1016/S1369-7021(04)00124-5)
- [2] D. Şopu et al. (2011): Deformation behavior of bulk and nanostructured metallic glasses studied via molecular dynamics simulations. Phys. Rev. B 83, 100202(R). <https://doi.org/10.1103/PhysRevB.83.100202>
- [3] M. Zink et al. (2006): Plastic deformation of metallic glasses: Size of shear transformation zones from molecular dynamics simulations. Phys. Rev. B 73, 172203. <https://doi.org/10.1103/PhysRevB.73.172203>
- [4] K. Albe et al. (2013): Enhancing the plasticity of metallic glasses: Shear band formation, nanocomposites and nanoglasses investigated by molecular dynamics simulations. Mech. Mater. 67, 94. <https://doi.org/10.1016/j.mechmat.2013.06.004>
- [5] J. X. Fang et al. (2012): Atomic Structure and Structural Stability of Sc₇₅Fe₂₅ Nanoglasses. Nano Lett. 12, 458. <https://doi.org/10.1021/nl2038216>
- [6] X. L. Wang et al. (2015): Plasticity of a scandium-based nanoglass. Scri. Mater. 98, 40. <https://doi.org/10.1016/j.scriptamat.2014.11.010>
- [7] R. Witte et al. (2013): Evidence for enhanced ferromagnetism in an iron-based nanoglass. Appl. Phys. Lett. 103, 073106. <https://doi.org/10.1063/1.4818493>
- [8] H. Gleiter and J. Beilstein (2013): Nanoglasses: a new kind of noncrystalline materials. Nanotechnol. 4, 517. <https://doi.org/10.3762/bjnano.4.61>
- [9] LAMMPS Molecular Dynamics Simulator <http://lammps.sandia.gov/>

Last Update: 2022-08-19 09:42