

Deformation Phenomena in Metallic Glass/High Entropy Nanolaminates

Project Manager
Dr. Daniel Sopu

Principal Investigator
Prof. Dr. rer. nat. Karsten Albe

Project Term
2022 - 2023

Clusters
Lichtenberg Cluster Darmstadt

Software
LAMMPS

Institute
Fachgebiet Materialmodellierung

University
Technische Universität Darmstadt




Figure 1: Stress-strain response, atomic strain and sign of rotation in CuZr MGs during athermal quasistatic shearing. (a) Stress-strain curve together with the evolution of the rotation field (in degrees). (b) A representative STZ in the elastic regime (highlighted by a dashed square in (a)) is analyzed in detail using the atomic strain and (c), the sign of the rotation angle. The atomic strain around the elastic events show a quadrupolar distribution. The rotation field generated by the complex strain distribution around the STZ shows also a quadrupolar-like shape. For a better visualization atoms of low strain/rotation have been removed (middle panels). A 3-dimensional representation of this elastic event is presented in the right-hand side panels.

Introduction

The application of metallic glasses (MGs) is limited by their brittle behavior at room temperature [1]. In order to underpin the potential of using MGs as structural materials, the shear bands generation and propagation from elastic excitation to plastic deformation must be further investigated. However, due to the spatial and temporal confinement [2], the dynamics of shear banding are typically difficult to study and even the most sophisticated atomistic simulation method could not perfectly establish a universal structure-plasticity picture. Hence, the atomic-level mechanism of elastic to plastic transition and, moreover, the effect of structural or stress fluctuations on the propagation of shear bands are still open for discussion.

Methods

In order to study the atomic-level mechanism of shear band propagation and remove the thermal noise effect, the deformation of monolithic Cu₆₄Zr₃₆ MG was investigated by performing athermal quasi-static (AQS) simulations. Furthermore, the structure and the stress modulated MG heterostructures were designed and deformed to investigate the effect of structural or stress fluctuations on the propagation of shear bands. The Cu₆₄Zr₃₆ MG system was relaxed at different temperatures starting from 50K up to the melting temperature with a temperature increment of 50K. In this way, the change of the structure and the stress states with temperature can be systematically investigated. Molecular dynamics (MD)

simulations were conducted using the LAMMPS software [3]. The deformation mechanisms were monitored using atomic the local entropy- based structural identification, von Mises strain and stress and the sign of rotation angle calculated and visualized using the OVITO analysis and visualization software using the python scripting interface [4].

Results

The first aim of this project was to disclose the atomic-level mechanism underlying elastic and plastic deformation in MGs. By simulating athermal quasistatic shearing processes, we concluded that shear transformation zones (STZ) start to activate from a very early stage of loading (see Fig. 1 a) and the variation in their magnitude defines the boundary between elastic and plastic events. During loading, elastic heterogeneities undergo a continuous distortion that generates small strain variations and elastic excitations. Eventually, the elastic events exceed the local yield stress and the energy overcomes the barrier for large plastic strain. In general, during STZ activation the complex strain and the corresponding directional rotation fields display quadrupolar distributions (Fig.1 b-c) with long-range signatures that overlap to some extent, constraining the atomic rearrangement during plastic, and even elastic unloading.

As the propagation of a shear band is a stress-driven process [5], we designed and tested the stress-modulated heterogeneity MG structures. The correlation between the deformation behavior and the effect of stress and structure heterogeneities in MGs was investigated. In general, strain hardening together with enhanced tensile ductility in monolithic MGs can be attained by only modulating the internal stress state without changing their local structure. The stress heterogeneity caused by the residual stresses can change the shear band dynamics leading to the formation and interaction of multiple shear bands, which consequently enhances the deformability. Moreover, the residual compressive stress offsets the external tensile stress, which delays shear band formation and, therefore, is responsible for efficient strain hardening and toughness.

Through systematic control of the annealing parameters, we have been able to simulate MGs resembling structures usually obtained by quenching at cooling rates used in the melt spinning process. Density, local order, and local entropy calculations predict MGs with structures prepared at cooling rate orders of magnitude lower than those typically realized in atomistic modeling. Hence, annealing above T_g is an alternative to melt quenching simulations and offers the prospect of modeling well relaxed glassy structures that were not achievable before in molecular dynamics simulations.

Discussion

Firstly, we reveal a novel and more complete perspective of STZ formation and evolution highlighting its Eshelby-like inclusions characteristics. The novel picture of STZs could pave the way towards developing better tools to understand and control the structure-property relationship in MGs. Moreover, this approach

allows to resolve the three-dimensional structural evolution of the complex STZ-vortex unit down to the atomic scale and to deepen the understanding of the fundamental deformation mechanisms of MGs from small elastic excitations to macroscopic plasticity. Secondly, our simulation result indicates that the strain-hardening of MGs can be achieved by only designing the internal stress state without changing its structure. The fact that MGs can overcome shear-softening mechanical behavior and achieve strain hardening and extensive ductility at room temperature without affecting structural order underpins the potential of using MGs as structural materials. Finally, we managed one critical issue associated with high cooling rates used to model MG structures. By systematically controlling the annealing temperature and time MGs with structures equivalent to those obtained by quenching at cooling rates used in melt spinning processes could be simulated.

Publications

Şopu, D.; Yuan, X.; Eckert, J. Annealing metallic glasses above T_g in order to accelerate the relaxation process in molecular dynamics simulations, *Appl. Phys. Lett.* 120.1 (2022)
https://ui.adsabs.harvard.edu/link_gateway/2022ApPhL.120a19045/doi:10.1063/5.0073204

Yuan, X.; Şopu, D.; Speickermann, F.; Song, K.K. ; Prashanth, K.G.; Ketov, S.V.; Eckert, J.; Maximizing the degree of rejuvenation in metallic glasses, *Scripta Mater.* 212 (2022)
<https://doi.org/10.1016/j.scriptamat.2022.114575>

Reference

[1] Hays, C.C.; Kim, C.P.; Johnson, W.L. Microstructure Controlled Shear Band Pattern Formation and Enhanced Plasticity of Bulk Metallic Glasses Containing in situ Formed Ductile Phase Dendrite Dispersions. *Phys. Rev. Lett.*, 84 (2000), pp. 2901-2904
<https://doi.org/10.1103/PhysRevLett.84.2901>

[2] Song, S.X.; Nieh, T.G.; Direct measurements of shear band propagation in metallic glasses – An overview. *Intermetallics*, 19 (2011), pp. 1968-1977 <https://doi.org/10.1016/j.intermet.2011.06.018>

[3] Liu, C.; Maaß, R. Elastic Fluctuations and Structural Heterogeneities in Metallic Glasses. *Adv. Funct. Mater.*, 28 (2018), Article 1800388
<https://doi.org/10.1002/adfm.201800388>

[4] Stukowski, A. Visualization and analysis of atomistic simulation data with OVITO—the Open Visualization Tool. *Model. Simul. Mater. Sci. Eng.*, 18 (2010), p. 15012
<https://iopscience.iop.org/article/10.1088/0965-0393/18/1/015012/meta>

[5] Şopu, D.; Moitzi, F.; Mousseau, N.; Eckert, J. An atomic-level perspective of shear band formation and interaction in monolithic metallic glasses. *Appl. Mater. Today*, 21 (2020) pp. 100828
<https://doi.org/10.1016/j.apmt.2020.100828>

Last Update: 2024-07-18 09:03